


PCT

WORLD INTELLECTUAL PRO
International I



INTERNATIONAL APPLICATION PUBLISHED UNDER

(51) International Patent Classification ⁶ :

B32B 27/08, 7/04, C08J 5/12, 7/06

A1

(11) 1

WO 9605964A1

(43) International Publication Date: 29 February 1996 (29.02.96)

(21) International Application Number: PCT/US95/08065

(22) International Filing Date: 26 June 1995 (26.06.95)

(30) Priority Data:
08/293,469 19 August 1994 (19.08.94) US

(71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventor: FUKUSHI, Tatsuo; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

(74) Agents: BRINK, Robert, H. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States: CA, CN, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

With international search report.

(54) Title: LAMINATE HAVING A FLUOROPOLYMER LAYER

(57) Abstract

A method for increasing the adhesion of a first layer comprising fluoropolymer to a second layer comprising a hydrocarbon polymer is disclosed. The method comprises coating an aliphatic di- or polyamine of less than 1,000 molecular onto at least one of the layers. The resulting multi-layer compositions and articles comprising the composition are also disclosed.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

LAMINATE HAVING A FLUOROPOLYMER LAYER

5

The invention relates to multi-layer compositions comprising a fluoropolymer layer, in particular, a fluoropolymer comprising interpolymerized units derived
10 from vinylidene fluoride. In another aspect, this invention relates to methods of improving the adhesion between the fluoropolymer layer and other dissimilar materials, such as polyamides or polyolefins.

Fluorine-containing polymers, or fluoropolymers,
15 are an important class of polymers and include for example, fluoroelastomers and fluoroplastics. Within this class are polymers of high thermal stability and usefulness at high temperatures, and extreme toughness and flexibility at very low temperatures. Many of
20 these polymers are almost totally insoluble in a wide variety of organic solvents. See, for example F.W. Billmeyer, Textbook of Polymer Science, 3rd ed., pp. 398-403, John Wiley & Sons, New York (1984).

Fluoroelastomers, particularly the copolymers of
25 vinylidene fluoride with other ethylenically unsaturated halogenated monomers, such as hexafluoropropene, have particular utility in high temperature applications, such as seals gaskets and linings. See, for example, Brullo, R.A.,
30 "Fluoroelastomer Rubber for Automotive Applications," Automotive Elastomer & Design, June 1985, "Fluoroelastomers Seal Up Automotive Future," Materials Engineering, October 1988, and "Fluorinated

Elastomers," Kirk-Othmer, Encyclopedia of Chemical Technology, 3rd ed., Vol. 8, pp. 500-515, John Wiley & Sons, New York (1979).

Fluoroplastics, particularly

- 5 polychlorotrifluoroethylene, polytetrafluoroethylene, copolymers of tetrafluoroethylene and hexafluoropropylene, and poly(vinylidene fluoride), have numerous electrical, mechanical, and chemical applications. Fluoroplastics are useful, for example,
10 in wire, electrical components, seals, solid and lined pipes, and pyroelectric detectors. See, for example, "Organic Fluorine Compounds," Kirk-Othmer, Encyclopedia of Chemical Technology, Vol. 11, pp. 20, 21, 32, 33, 40, 41, 48, 50, 52, 62, 70, and 71, John Wiley & Sons,
15 New York (1980).

Increased concerns with evaporative fuel standards have led to a need for fuel system components that have increased barrier properties to minimize the permeation of fuel vapors through automotive components such as
20 fuel filler lines, fuel supply lines, fuel tanks, and other components of the emission control system of the engine. Various types of tubing have been proposed to address these concerns. In general, the most successful of these have been co-extruded multi-layer
25 tubing.

Multi-layer compositions comprising a fluorinated polymer layer and a polyamide or polyolefin layer are known. See, for example, U.S. Pat. No. 4,933,090 (Krevor) which discloses laminate tubular articles
30 which can comprise layers of fluorocarbon elastomers, and PCT Publication WO 93/1493 (LaCourt) which discloses a laminar film structure comprising a polyimide and a fluoropolymer.

A variety of methods have been used to increase the adhesion between a fluorinated polymer layer and a polyamide or polyolefin layer. For example, an adhesive layer can be added between the two polymer layers. U.S. 5,047,287 discloses a diaphragm, suitable for use in automotive applications, which comprises a base fabric having bonded to at least one surface a fluororubber layer by an adhesive which includes an acrylonitrile-butadiene or acrylonitrile-isoprene rubber having an amino group. See also, for example, European Patent Application 05595445 (Nishino et al.), UK Patent 2,204,932 (Washizu). See also U.S. 5,242,976 (Strassel et al.) which discloses coextruding vinylidene polyfluoride with an alkyl polymethacrylate and vinylidene polyfluoride composition.

Sometimes surface treatment of one or both of the layers is used to help increase bonding. For example, fluoropolymer layers have been treated with charged gaseous atmosphere followed by applying a layer of a second material, for example thermoplastic polyamide. See, for example, European Patent Applications 0185590 (Ueno et al.) and 0551094 (Krause et al.) and U.S. Pat. Nos. 4,933,060 (Prohaska et al.) and 5,170,011 (Martucci).

Blends of the two layers are sometimes used as an intermediate layer to help bond the two layers together. European Patent Application 0523644 (Kawashima et al.) discloses a plastic laminate having a polyamide resin surface layer and a fluororesin surface layer. The application states that it is difficult to make laminates having a polyamide layer and a fluororesin layer due to the incompatibility of the two materials. The laminate is prepared by the use of an intermediate layer of a blend of an aliphatic

polyamide resin with a fluorine-containing graft copolymer.

Summary of the Invention

5 Briefly, in one aspect, the present invention provides a method for increasing the adhesion of a first layer comprising fluoropolymer to a second layer comprising hydrocarbon polymer, comprising the steps of coating onto at least one face of at least one of said
10 layers a composition comprising an aliphatic di- or polyamine of less than 1,000 molecular weight; and placing said layers together such that said amine composition is in contact with and between the two layers; wherein said fluoropolymer comprises
15 interpolymerized units derived from vinylidene fluoride, said hydrocarbon polymer is a polyamide, polyimide, or a carboxyl, anhydride, or imide functional polyolefin, and said di- or polyamine is present in an amount sufficient to increase the
20 adhesion between the two layers compared to compositions without said di- or polyamine. Preferably said first layer is predominately fluoropolymer and said second layer is predominately hydrocarbon polymers. Sometimes, in order to obtain sufficient
25 adhesion, it may be desirable or necessary to further treat the resulting multi-layer composition, for example by additional heat or pressure.

 In another aspect, the present invention provides a multi-layer composition comprising a first layer
30 comprising fluoropolymer, a second layer comprising hydrocarbon polymer, and an aliphatic di- or polyamine of less than 1,000 molecular weight, wherein said fluoropolymer comprises interpolymerized units derived from vinylidene fluoride, said hydrocarbon polymer is a

polyamide, polyimide, or a carboxyl, anhydride, or imide functional polyolefin, substantially all of said amine is located between and in contact with said two layers, and said amine is present in an amount
5 sufficient to increase the adhesion between said layers compared to compositions without said di- or polyamine. The invention also provides articles comprising the compositions of this invention. Preferably said first layer is predominately fluoropolymers and said second
10 layer is predominately hydrocarbon polymers.

The methods of this invention provide multi-layer compositions with improved inter-layer adhesion. The methods and compositions of this invention are particularly useful for making articles, such as tubing
15 and hoses, suitable for use in motor vehicles, for example as fuel-line hoses.

Detailed Description

Fluoropolymer materials suitable for use in this
20 invention are those comprising interpolymerized units derived from vinylidene fluoride ("VF₂" or "VDF"). Preferably such polymers comprise at least 3% by weight of interpolymerized units derived from VF₂. Such polymers may be homopolymers of VF₂ or copolymers of VF₂
25 and other ethylenically unsaturated monomers.

Such VF₂ polymers and copolymers can be made by well-known conventional means, for example by free-radical polymerization of VF₂ with or without other ethylenically-unsaturated monomers. For example, the
30 preparation of colloidal, aqueous dispersions of such polymers and copolymers is described, for example, in U.S. Pat. No. 4,335,238. It follows the customary

process for copolymerizing fluorinated olefins in aqueous, colloidal dispersions, which is carried out in the presence of water-soluble initiators which produce free radicals, such as, for example, ammonium or alkali metal persulfates or alkali metal permanganates, and in the presence of emulsifiers, such as, in particular, the ammonium or alkali metal salts of perfluorooctanoic acid. Useful fluorine-containing monomers include hexafluoropropene (HFP), tetrafluoroethylene (TFE), chlorotrifluoroethylene (CTFE), 2-chloropentafluoropropene, perfluoroalkyl vinyl ethers, e.g. $\text{CF}_3\text{OCF}=\text{CF}_2$ or $\text{CF}_3\text{CF}_2\text{OCF}=\text{CF}_2$, 1-hydropentafluoropropene, 2-hydropentafluoropropene, dichlorodifluoroethylene, trifluoroethylene, 1,1-dichlorofluoroethylene, vinyl fluoride, and perfluoro-1,3-dioxoles such as those described in U.S. Pat. No. 4,558,142 (Squire). Certain fluorine-containing di-olefins are also useful, such as perfluorodiallylether and perfluoro-1,3-butadiene. Said fluorine-containing monomer may also be copolymerized with fluorine-free terminally unsaturated monoolefin comonomers, e.g., ethylene or propylene. Preferably at least 50% by weight of all monomers in a polymerizable mixture are fluorine-containing. Said fluorine-containing monomer may also be copolymerized with iodine- or bromine-containing cure-site monomers in order to prepare peroxide curable polymer. Suitable cure-site monomers include terminally unsaturated monoolefins of 2 to 4 carbon atoms such as bromodifluoroethylene, bromotrifluoroethylene, iodotrifluoroethylene, and 4-bromo-3,3,4,4-tetrafluorobutene-1.

Useful fluoropolymer materials include commercially available fluoropolymers, for example, THV 500 fluoropolymer (available from 3M), Kynar™ 740 fluoropolymer (available from Atochem), and Fluorel™ FC-2178 fluoropolymer (available from 3M).

The di- or polyamines useful in this invention are aliphatic amines of molecular weight less than 1,000. By "aliphatic" is meant that the nitrogen atoms of at least two amines in the compound are bonded directly to only hydrogens or to aliphatic carbon atoms rather than being bonded directly to aromatic moieties or functional groups (e.g., carboxyl). For example, as "aliphatic amine" is used in this specification and claims, aniline and urea are not aliphatic amines. Secondly, amines are more preferred than tertiary amines and primary amines are most preferred. Most preferred are alkylene polyamines or diamines, such as hexamethylene diamine and dodecyl diamine, comprising at least 2 primary amines.

Polyamides useful as the hydrocarbon layer are generally commercially available. For example, polyamides such as any of the well-known Nylons are available from a number of sources. Particularly preferred polyamides are nylon 6, nylon 6,6, nylon 11, or nylon 12. It should be noted that the selection of a particular polyamide material should be based upon the physical requirements of the particular application for the resulting article. For example, nylon 6 and nylon 6,6 offer higher heat resistant properties than nylon 11 or nylon 12, whereas nylon 11 and nylon 12 offer better chemical resistant properties. In addition to those polyamide materials, other nylon material such as nylon 6,12, nylon 6,9, nylon 4, nylon

4,2, nylon 4,6, nylon 7, and nylon 8 may also be used. Ring containing polyamides, e.g., nylon 6,T and nylon 6,I may also be used. Polyether-based polyamides, such as Pebax™ polyamides may also be used.

5 The polyolefin polymers are generally homopolymers or copolymers of ethylene or propylene, for example, copolymers with vinyl acetate or acrylic monomers. Carboxyl, anhydride, or imide, functionalities are generally incorporated into the polyolefin by
10 copolymerizing with functional monomers, for example, acrylic acid or maleic anhydride, or by modifying a polyolefin after polymerization. The carboxyl, anhydride, or imide functional polyolefins useful as the hydrocarbon layer are generally commercially
15 available. For example, acid modified ethylene vinyl acetates, acid modified ethylene acrylates, anhydride modified ethylene acrylates, anhydride modified ethylene vinyl acetates, anhydride modified polyethylenes, and anhydride modified polypropylenes
20 are available from DuPont, Wilmington, Delaware as Bynel™ coextrudable adhesive resins.

Coating of the di- or polyamine may be by conventional means. For example, one useful method is to place the di- or polyamine in a solution which is
25 coated onto the fluoropolymer layer, the hydrocarbon layer, or both. The two layers can then be brought together by any suitable method, such as, for example, extrusion coating or lamination. Other standard coating methods which can be used include brushing,
30 spraying, roll-coating, and extruding (generally a melt).

The heat and pressure of the method by which the layers are brought together, may be adequate to provide sufficient adhesion. However, it may be desirable to further treat the resulting multi-layer composition, for example, with additional heat or pressure or both. One way of supplying extra heat when the multi-layer composition is prepared by extrusion is by delaying the cooling of the composition because the composite is hot as a result of the extrusion process. Where additional heating or pressure is desired, it may be accomplished by performing the steps of applying or extruding at a temperature higher than necessary for merely processing the several components. Alternatively, the finished article may be held at an elevated temperature for an extended period of time, or the finished article may be placed in a separate means for elevating the temperature of the article, such as an oven or heated liquid bath. A combination of these methods may also be used.

The methods of this invention provide multi-layer compositions with improved inter-layer adhesion. The methods and compositions of this invention are particularly useful for making articles, such as tubing and hoses, suitable for use in motor vehicles, for example as fuel-line hoses, and for films and blow-molded articles such as bottles where chemical resistance or barrier properties are important. The two-layer compositions of this invention are useful in preparing three- or more-layer compositions. For example, a three layer composition of fluoropolymer to anhydride modified polyolefin to unmodified polyolefin could be prepared might be useful as a gasket or diaphragm.

Examples

In the following Examples and Comparative Examples various multi-layer compositions were prepared and the adhesion between the layers was evaluated. All concentrations and percentages are by weight unless otherwise indicated.

Example 1

A 5% solution of hexamethylene diamine (HMDA) was made by dissolving 0.5 g of HMDA, available from Aldrich Chemical Co., in 9.5 g of E.P. grade methanol. This 5% HMDA solution was coated, using a paint brush, onto a 4 inch by 4 inch (10 cm by 10 cm) sheet of 18 mil (457 micro meters) thick Vestamid™ L2140 nylon film made from resin available from Hüls Aktiengesellschaft. After the coated sheet was allowed to dry at room temperature, the coating weight of HMDA on the nylon was determined, by weighing the coated sheet, to be 1.1 mg/cm². Then, 3 layers of 10 mil (about 254 micro meters) thick sheets of THV 500 film, a terpolymer of TFE, HFP, and VDF, made from resin available from 3M Co., for a total THV 500 thickness of 30 mils (762 micro meters), was applied to the HMDA coated side of the nylon and the composite was heated under pressure using a Wabash Hydraulic Press Co. heated platen press at 177°C and 3.5 psi (about 24 kPa) for 3 minutes. The sample was removed from the press and allowed to cool to room temperature. The resulting sample was cut into three 1-inch wide (2.54 cm) strips. Peel strength or adhesion was measured on the three strips in accordance with ASTM D 1876 (T-Peel Test).

To facilitate testing of the adhesion between the layers via a T-peel test, a sheet of 3 mil (76 micro meters) thick polyester (PET) film coated with a

silicone release agent was inserted about 2.54 cm between the coated nylon 12 layer and the THV layer along one edge of the 10 cm X 10 cm sample. The sheet of PET did not adhere to either material and was used only to create a THV "tab" and a nylon 12 "tab" to insert into the jaws of a test device. An Instron Model 1125 at 100 mm/min crosshead speed was used as the test device. If there were many peaks recorded on the graph from the T-peel test, the peel strength was calculated in accordance with ISO 6133-'81. The results of the three samples were averaged. The average of the three peel strength values obtained was 17.4 kg/in. The test results are summarized in Table 1.

15

Examples 2-11

In Examples 2-11, samples were prepared and tested as in Example 1 except that press time in minutes, temperature in °C, and the concentration of HMDA in weight % of solids were varied as shown Table 1. Also, Example 4 was made using the higher pressure of 6 MPa. The measured values of peel strength are also summarized in Table 1.

25 Comparative Examples C1-C5

In Comparative Examples C1 and C2, samples were prepared and tested as in Example 1 except the nylon 12 sheets were not coated with the HMDA solution. In Comparative Examples C3 and C4, samples were prepared and tested as in Example 1 except the coating on the nylon 12 sheets was only methanol. No HMDA was in the solution. In Comparative Example C5, samples were prepared and tested as in Example 1 except the HMDA was

applied as a 1% solution and the press time was 1 minute. The test results are summarized in Table 1.

Table 1

Example #	Coating conc. (%)	Temp. °C	Time (Min.)	Peel (kg/in.)
1	5	177	3	17.4
2	5	177	1	4.0
3	5	177	6	22.5
4	5	177	3	22.5
5	5	163	3	12.4
6	5	190	3	29.5
7	1	177	3	3.0
8	1	177	6	3.2
9	2	177	3	9.8
10	10	177	3	27.5
11	30	177	3	29.5
C1	-	177	3	0.2
C2	-	177	6	0.2
C3	0	177	3	0.2
C4	0	177	6	0.2
C5	1	177	1	0.1

5 The data in Table 1 show that samples coated with the diamine-containing solutions provide improved peel strength compared to samples without diamine. The time
10 at the indicated temperature is important, as is the diamine concentration.

Examples 12-24

In Examples 12-24, samples were prepared and tested as in Example 1 except that the HMDA solution was replaced by a 5% solution of various materials listed in Table 2. The test results and materials used are summarized in Table 3.

Table 2

	<u>Chemical</u>	<u>Source</u>
10	1,12-dodecyl diamine (DDDA)	AC
	diethylene triamine (DETA)	AC
	ketimine of DETA (Epon™ H3)	SC
	N,N'-dicinnamylidene-1,6-hexandiamine (Diak™ #3)	D
	1,3-diamino-2-hydropropane (DAHP)	AC
15	2,4-diamino-6-methyl-1,3,5-triazine (DAMT)	AC
	1,4-bis(3-aminopropyl)-piperazine (BAPP)	AC
	4,4'-methylene bis-(cyclohexylamine) (MBCHA)	AC
	4,4'-ethylenedianiline (EDA)	AC
	Tris(2-aminoethyl)amine (TAEA)	AC
20	polyether diamine (Jeffamine™ EDR-148)	TC
	1,3-bis(3-aminopropyl)-	
	-tetramethyldisiloxane (BAPTS)	SL
	3-aminopropyltriethoxysilane (A-1100)	UC
	N,N'-dimethylhexanediamine (DMHDA)	AC
25	N,N,N',N'-tetramethyl-hexanediamine (TMHDA)	AC
	hexyl amine	AC
	urea	AC
	melamine	AC
	triphenyl benzyl phosphonium chloride (TPBPCl)	

30

AC means Aldrich Chemical Company. D means E. I. DuPont de Nemours Co. SC means Shell Chemical Co. TC means Texaco, Inc. SL means Silar Laboratories, Inc. UC means Union Carbide

Table 3

Example #	Coating Solids	Time (Min.)	Peel (kg/in.)
12	DDDA	3	16.4
13	DETA	3	14.4
14	Epon™ H3	3	16.0
15	Diak™ #3	3	15.6
16	DAHP	3	14.8
17	BAPP	3	15.9
18	MBCHA	3	12.9
19	TAEA	3	16.4
20	Jeffamine™ EDR-148	3	18.4
21	BAPTS	3	18.3
22	A-1100	3	20.0
23	DMHDA	3	13.2
24	TPBPCl HMDA	1	9.3

5

The data in Table 3 show that many other aliphatic diamines also dramatically increase the peel strength between the layers compared to samples without aliphatic diamine (see, e.g., data in Table 4). Note that the compounds used in Examples 14 and 15 are blocked amines that form primary amines upon heating or moisture. Note the silane used in Example 22 condenses within itself to form di- or polyamines.

15 Comparative Examples C6 and C7

In Comparative Examples C6 and C7, samples were prepared and tested as in Example 1 except the coating was a 5% solids solution of hexyl amine instead of

HMDA. The components, process conditions, and test results are summarized in Table 4.

Comparative Examples C8-C15

5 In Comparative Examples C8-C15, samples were prepared and tested as in Example 1 except the coating solutions contained amine components which were not di- or poly-amine functional, or which contained only tertiary amine functionality, or contained some aromatic nature,
10 or were not aliphatic or alkyl substituted amines. The components, process conditions, and test results are summarized in Table 4. Also, the EDA was dissolved in tetrahydrofuran (THF) instead of methanol.

15

Table 4

Example #	Coating Solids	Time (Min.)	Peel (kg/in.)
C6	hexyl amine	3	0.2
C7	hexyl amine	6	0.2
C8	EDA	3	0.2
C9	EDA	6	0.2
C10	Urea	3	0.2
C11	Melamine	3	0.1
C12	DAMT	3	0.1
C13	TMHDA	3	0.2
C14	TMHDA	6	0.4

The data in Table 4 show that primary mono-amines, such as hexyl amine (Comparative Examples C6 and C7 do
20 not give significantly improved adhesion values. Aromatic-containing diamines, such as, for example those used in Comparative Examples C8, C9, and C11, do

not give significantly improved adhesion. Amines containing only tertiary amines, such as, for example, the amines used in Comparative Examples C13 and C14, also do not give significantly improved adhesion.

- 5 Non-alkyl substituted amines, such as, for example, the amine used in Comparative Example C10, also do not give acceptable adhesion.

Examples 25 and 26

- 10 In Examples 25 and 26, samples were made which contained a sheet of elastomer instead of the sheet of nylon 12 used in Example 1. The ingredients used in each sheet of elastomer were compounded on a two-roll mill using conventional methods. The compositions of
15 the compounded elastomer sheets are shown in Table 3. All amounts referred to therein are in parts per 100 parts by weight rubber abbreviated "phr". Table 6 lists the sources for the ingredients in Table 5. A sheet about 2 mm thick was formed from each elastomer
20 composition by using a two-roll mill. Samples of the invention were then prepared as in Example 1 except using the above prepared elastomer sheets instead of the nylon 12 sheet. The samples were then held in the press at 177°C for 6 minutes instead of 3 minutes. The
25 adhesion results of Examples 25 and 26 are shown in Table 7.

Table 5 - Formulation of Various Elastomers

	<u>ACM</u>	<u>Vamac</u>
5 Hytemp TM 4051EP	100	
Vamac TM HGB-124		124
N-774 Carbon Black		35
N-550 Carbon Black	65	
Stearic Acid	1	2
10 Armeen 18D		0.5
Diak #1		1.25
Diak #3	3	
AgeRite Stalite S	1	
Diphenylguanidine		4
15		

Table 6

<u>Chemical</u>	<u>Source</u>
Hytemp TM 4051EP (acrylic ester copolymer)	Zeon Chemical
20 Vamac TM HGB-124 (ethylene/acrylic rubber)	E.I. DuPont
Stearic acid	EM Science
Armeen TM 18D (octadecyl amine)	Armak Co.
Diak TM #1 (hexamethylene diamine carbamate)	DuPont
25 Diak TM #3 (See Table 2)	
AgeRite Stalite TM S (mixture of octylated diphenylamine)	R.T. Vanderbilt
DPG (diphenyl guanidine)	American Cyanamid

Table 7

Example #	Substrate	Time (Min.)	Peel (kg/in.)
25	ACM	6	9.0
26	Vamac™	6	11.6

The data in Table 7 show that the methods of this invention also result in greater adhesion between fluoropolymer layers and polyolefins containing carboxyl functionality.

Examples 27 and 28

10 In Examples 27 to 28, samples were prepared and tested as in described in Example 1 except that a 127 micro meter thick sheet (5 mil) of Kapton™ polyimide film, DuPont, and Kevlar™ aramid fiber in a woven fabric (available from DuPont) were used instead
15 of nylon as the hydrocarbon polymer component. The results are shown in Table 8.

Table 8

Example #	Substrate	Peel (kg/in.)
27	Kapton™	1.5
28	Kevlar™	0.7

20 The data in Table 8 show that the methods of this invention are useful for increasing the bonding to aromatic polyamides and to polyamides.

Example 29

25 In Example 29, a sample was prepared and tested as in Example 1 except a 10 mil (254 micro meters) thick sheet of Bynel™ 4003 anhydride-modified high density

polyethylene (AM-HDPE), resin available from DuPont, was used instead of nylon 12. Film of Bynel™ 4003 was prepared by press-molding the resin in a heated platten press at 177°C. The substrate and the test results are summarized in Table 9.

Example 30

In Example 30, a sample was made as in Example 29 except the 5% HMDA solution was coated on a sheet of Bynel™ 1123 acid-modified ethylene vinylacetate copolymer (AC-EVA), resin available from DuPont, instead of the nylon 12 sheet. A sheet of polystyrene (PS) film, available from Aldrich Chemical, was added to the composite on the uncoated side of the acid-modified ethylene vinylacetate copolymer sheet at 177°C for 3 minutes. The peel strength was tested between the AC-EVA and the THV layers by grasping the THV layer in one jaw and the AC-EVA and PS layers in the other jaw. The substrate and the test results are summarized in Table 9.

Examples 31 and 32

In Examples 31 and 32, samples were prepared and tested in a same manner as described in Example 30 except Bynel™ E374 anhydride-modified ethylene vinylacetate copolymer (AM-EVA), available from DuPont, was used for bonding to polycarbonate (PC) film, in Example 32 and for bonding to polyethylene terephthalate (PET) film in Example 33. PC resin and the PET resin are available from Aldrich Chemical. PC film and PET film were prepared as in Example 30, except the platen press was heated to 250°C. The peel strength was tested between the AM-EVA and the THV

layers by grouping the layers as in Example 30. The substrates and the test results are summarized in Table 9.

5 Comparative Examples C15 and C16

In Comparative Example C15, a sample was made and tested as in Example 29 except a 10 mil (254 micro meters) thick sheet of LS901046 HDPE, resin available from Quantum, was used instead of the sheet of
10 nylon 12.

In Comparative Example C16, a sample was made and tested as in Comparative Example C15 except a 10 mil (254 micro meters) thick sheet of Bynel™ 4003 AM-HDPE, resin available from DuPont, was used and was not
15 coated with any HMDA solution. The substrates and the test results are summarized in Table 9.

The test results and process conditions are shown in Table 9.

20

Table 9

Example #	Substrate	Peel (kg/in.)
29	Bynel™ 4003 AM-HDPE	8.2
30	Bynel™ 1123 AC-EVA /PS	3.4
31	Bynel™ E374 AM-EVA /PC	8.2
32	Bynel™ E374 AM-EVA /PET	1.5
C15	HDPE	FA
C16	Bynel™ 4003 AM-HDPE	FA

The data in Table 9 show that polyethylene without carboxy, amide, or anhydride functionality is not useful in the method of this invention.

- 5 "FA" means the sample fell apart before they could be tested.

Example 33

10 In Example 33, a sample was prepared as in Example 1 except a 1 mm thick sheet of 680 denier nylon 6 fabric was used instead of the nylon 12 sheet. Even though the coating was applied to only one side of the fabric, the porosity of the fabric allowed some of the coating solution to reach the other, uncoated side of the
15 fabric. Then, 30 mils (about 762 micro meters) of THV 500 film was applied to each side of the nylon fabric, using the press cycle and conditions of Example 1. The test for adhesion was done between the THV 500 film, which was applied to the purposely coated side of the
20 fabric, and the fabric. The substrate and the test results are summarized in Table 11.

Example 34-37

25 In Examples 34-37, samples were prepared and tested as in Example 1 except that the 30 mils (about 762 micro meters) of fluoropolymer film were made from THV 200 resin, available from 3M, instead of THV 500 resin. Also, different temperatures were used in the 3 minute press cycle as shown in Table 10. THV 200 is
30 also a terpolymer of TFE, HFP, and VDF, but with a monomer unit ratio of 42, 20 and 38 respectively. The substrates and the test results are summarized in Table 11.

Example 38

In Example 38, a sample was prepared and tested as in Example 1 except that THV 400 resin, available from 3M, was used instead of THV 500 resin. THV 400 is also a terpolymer of TFE, HFP, and VDF, but with a monomer unit ratio of 53, 18 and 29 respectively. The substrate and the test results are summarized in Table 11.

10 Example 39-41

In Examples 39-41, samples were prepared and tested as in Example 1 except that fluoroelastomer sheets of about 2 mm thickness were used instead of the THV 500 sheets. The 2 mm thick sheets were formed using a two-roll mill. Fluorel™ FC-2178 is a copolymer of VDF and HFP available from 3M. Fluoroelastomer A (FE-A) is a terpolymer of VDF, HFP and TFE with a Mooney viscosity ML (1+10) 121°C greater than 100. Fluoroelastomer B (FE-B) is a terpolymer of VDF, propylene (P) and TFE with a Mooney viscosity ML (1+10) 121°C of 60. FE-A and FE-B were made using conventional polymerization techniques and the resulting monomer unit ratios determined by NMR are listed in Table 10. The substrate and the test results are summarized in Table 11.

Table 10

Monomer composition (wt%) (as determined by NMR)

	<u>Fluoroelastomer</u>	<u>VDF</u>	<u>HFP</u>	<u>TFE</u>	<u>P</u>	<u>Supplier</u>
30	Fluorel™ FC-2178	62	38	-	-	3M
	Fluoroelastomer A	41	35	24	-	experimental
	Fluoroelastomer B	3	-	74	23	experimental

The results and process conditions of Examples 34-42 are summarized in Table 11. All samples were held for three minutes at a pressure of 24 kPa in the press.

5 Comparative Examples C17 to C19

In Comparative Examples C17 to C19, samples were prepared and tested as in Example 1 except no diamine solution was coated on the nylon.

10

Table 11

Example #	Fluoropolymer Substrate	Temperature °C	Peel (kg/in.)
33	THV 500	177	4.0
34	THV 200	121	0.4
35	THV 200	149	7.1
36	THV 200	162	17.0
37	THV 200	177	24.2
38	THV 400	177	10.7
39	FC-2178	177	8.8
40	FE-A	177	6.6
41	FE-B	177	1.0
C17	FC-2178	177	0.4
C18	FE-A	177	0.4
C19	FE-B	177	0.1

The data in Table 11 show that fluoropolymer sheets containing VDF monomer ratios as low as 3% by wt. will improve the adhesion to polyamides when used with a diamine adhesion enhancer. Also, sufficient temperature is often needed to properly develop the adhesion. Examples 39-41 and Comparative Examples C17-15 C19 did not contain any curatives. After pressing at

177°C for 3 minutes, the fluoroelastomers were not cured. In Examples 39-41, the fluoropolymer tab broke during the peel test rather than separating from the coated nylon 12 substrate, thus indicating a peel strength greater than shown in Table 11.

Example 42-47

In Examples 42-47, samples were prepared and tested as in Example 1 except the fluoropolymers shown in Table 12 were used instead of the THV 500 sheets. CTFE is chlorotrifluoroethylene, and PVDF is polyvinylidene fluoride. The fluoropolymers used and the test results are summarized in Table 13.

Table 12

<u>Fluoropolymer</u>	<u>Composition</u>	<u>Monomer Ratio (wt%)</u>	<u>Supplier</u>
Kel-FTM KF-800	VDF/CTFE	15/85	3M
Kynar™ 740	PVDF	100	Atochem
Kynar™ 2800	VDF/HFP	90/10	Atochem
Cefral soft™	VDF/HFP grafted PVDF	unknown	Central Glass

Example 48

In Example 48, a sample was prepared and tested as in Example 1 except the fluoropolymer sheet was made from 41 g of THV 500 and 41 g of Tefzel™ 210 ETFE which were mixed using a Haake Rheomix™ 600 internal mixer with roller blades at 320°C for 6 minutes. The mixture was then molded at 270°C to make a sheet about 10 mils (254 micro meters) thick. The molded sheet was then prepared and tested in same way as described in Example 1. The fluoropolymers used and the test results are summarized in Table 13.

Comparative Example C20

In Comparative Example C20, a sample was prepared and tested as in Example 43 except without any HMDA. Test results are summarized in Table 13.

All samples were run at a pressure of 24 kPa.

Table 13

Example #	Substrate	Time (Min.)	Peel (kg/in.)
42	Kel-F™ 800	3	6.2
43	Kynar™ 740	3	1.0
44	Kynar™ 2800	3	0.8
45	Kynar™ 2800	10	7.3
46	Cefral soft™	3	0.4
47	THV 500/ Tefzel™ 210 50/50 blend	3	2.3
C20	Kel-F™ KF-800	3	0.4

10

The data in Table 13 show improved adhesion when fluoropolymers containing VDF monomer units are used in the method of this invention.

15 Comparative Examples C21-C28

In Comparative Examples C21-C28, samples were prepared and tested as in Example 1 except the fluoropolymer sheets were made with materials which did not contain VDF monomer units. The temperature used to press the samples was 177°C except for Comparative Example C22 which was pressed at 270°C. The fluoropolymer sheet thickness was about 10 mils (254 micro meters) and prepared by molding. Tefzel™ copolymer is a copolymer of ethylene and TFE (ETFE),

available from DuPont. Aflon COP™ C-88A copolymer and Aflon LM™ 740 ACOP are copolymers of ethylene and TFE available from Asahi Glass. Halar™ copolymer is a copolymer of CTFE and ethylene (ECTFE) available from Ausimonte. Teflon™ PFA is a copolymer of TFE and perfluoroalkylvinylether available from DuPont and Teflon™ FEP is a copolymer of TFE and hexafluoropropylene (HFP) also available from DuPont. Comparative Example C28 used a 25 micro meter film of Tedlar™ polyvinyl fluoride (PVF), available from DuPont. The fluoropolymer used and the test results are summarized in Table 14.

Table 14

Example #	Fluoropolymer	Time (Min.)	Pressure (kPa)	Peel (kg/in.)
C21	Tefzel™ 210	3	24	FA
C22	Tefzel™ 210	3	24	FA
C23	Aflon COP™ C-88A	3	24	FA
C24	Aflon LM™ 740ACOP	3	24	FA
C25	Halar™ ECTFE	3	24	FA
C26	Teflon™ PFA	3	24	FA
C27	Teflon™ FEP	3	24	FA
C28	Tedlar™ PVF	20	5	FA

15

The data in Table 14 show no measurable peel strength was achieved between the above non-VDF monomer unit-containing fluoropolymer materials and the polyamide sheets even with the HMDA coating applied. "FA" means the sample fell apart before they could be tested.

20

Various modifications and alterations of this invention will be apparent to those skilled in the art without departing from the scope and spirit of this invention and this invention should not be restricted
5 to that set forth herein for illustrative purposes.

What is Claimed is:

1. A method for increasing the adhesion of a first layer comprising fluoropolymer to a second layer comprising hydrocarbon polymer, comprising the steps of
 - (a) coating onto at least one face of at least one of said layers a composition comprising an aliphatic di- or polyamine of less than 1,000 molecular weight;
 - (b) placing said layers together to form a multi-layer composition such that said amine composition is between and in contact with the two layers;wherein said fluoropolymer comprises at least 3% by weight of interpolymerized units derived from vinylidene fluoride, said hydrocarbon polymer is a polyamide, polyimide, or a carboxyl, anhydride, or imide, functional polyolefin, and said di- or polyamine is present in an amount sufficient to increase the adhesion between the two layers compared to compositions without said di- or polyamine.
2. The method of Claim 1 wherein said amine is an alkylene diamine, said second layer is thermoplastic, said first layer consists predominately of fluoropolymers, and said second layer consists predominately of hydrocarbon polymers.

3. A multi-layer composition comprising a first layer comprising a fluoroplastic, a second layer in contact with said first layer comprising a hydrocarbon polymer, and an alkylene di-primary amine of less than
5 1,000 molecular weight, wherein said fluoroplastic comprises interpolymerized units derived from vinylidene fluoride, said hydrocarbon polymer is a polyamide, polyimide, or a carboxyl, anhydride, or imide functional polyolefin, substantially all of said
10 amine is located between and in contact with said two layers, and said amine is present in an amount sufficient to increase the adhesion between said layers compared to compositions without said amine.

INTERNATIONAL SEARCH REPORT

Inter. Application No

PCT/US 95/08065

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B32B27/08 B32B7/04 C08J5/12 C08J7/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08J B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US-A-5 047 287 (HORIUCHI NORIYUKI ET AL) 10 September 1991 cited in the application see column 1, line 50 - line 59; claim 1 ---	1-3
A	US-A-4 234 644 (BLAKE STEPHEN D ET AL) 18 November 1980 see column 4, line 24 - line 68; figure 1 ---	1-3
A	EP,A,0 597 120 (DAIKIN IND LTD) 18 May 1994 see page 3, line 46 - line 49; claims see page 4, line 15 - line 21 -----	1-3

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 August 1995

Date of mailing of the international search report

24 -08- 1995

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Pamies Oille, S

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/08065

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5047287	10-09-91	JP-A- 1177447	13-07-89
US-A-4234644	18-11-80	NONE	
EP-A-0597120	18-05-94	WO-A- 9324299	09-12-93